DRY

DRYFALL PAINT

757 Series

Latex Acrylic

Technical Data Sheet

PEINTURES

DESCRIPTION

A latex acrylic based dryfall paint developed for spraying commercial and warehouse ceilings.

CHARACTERISTICS	TECHNICAL INF	ORMATIO	N	
When applied at a height exceeding 15 feet, with a 50% humidity level, any dryfall paint particles that have fallen to the floor may be swept away with a broom or vacuumed. Coloured bases must be applied at a height exceeding 18 feet.	Drying Time	Recoat: 3	s	To touch: 15-30 min
This latex based product emits a very faint odour and is not a		Relative humidity at 50% May differ depending on the colour		
fire hazard.	Surface Coverage	56 m² (600 pi²) for steel deck ceilings with ceiling joists		
This dryfall paint will prevent flash rust from appearing on the surface during the application.		112 m² (1200 pi²) for a flat ceiling		
Not a health hazard This paint does not contain crystalline silica.	Cleaning	Lukewarm soapy water		
	Dilution	None		
	Solids by Weight	55%		
	Solids by Volume	38%		
	VOC	< 50 g/L	1	
	GLOSS	60° 85°	2.5% 3.5%	
	Flat	II.	i,	the texture of surface
TINTING BASES FORMATS	STANDARDS			
946ml 3.78L 18.9L Neutral white 757-8 X				
Base D 757-4 X Base A 757-5 X	MPI: Certified category #118			
Jacon Torio	(Master Paint Ins	stitute)		
COLOURS	0514 4			
Super White as well as bases 4,5, & 8.	CFIA: Approved product			
Neutral White (2oz max of colorant/ 3,78L) Base D (8oz max of colorant/ 3,78L)	(Canadian Food	Inspection .	Agency)	
Base A (12oz max of colorant/ 3,78L)				

USE	LIMITATIONS		
- For interior use	- Do not apply if temperature is below 10°C		
 Developed for galvanized steel or other metal structured ceilings more than 15 feet high and 18 	- Will not protect against rust in a humid area		
feet high for coloured bases Can be used on bare or painted surfaces	 Depending on the height of the ceiling, it is preferable to cover the floor, when the relative humidity is higher 		
- Suitable for both commercial or institutional projects	than 50%.		

SURFACE PREPARATION

The surface must be dry and clean, without dust, oil, grease, rust and soap. On painted surfaces, it is recommended to clean with T.S.P. (trisodium phosphate) in order to eliminate any contaminant that might harm the adhesion or the hardening of the product. Glossy surfaces must be sanded and dusted before painting.

SUGGESTED PRIMER

A primer is not required.

APPLICATION

Stir thoroughly before applying. It is important to keep the humidity level above 50%, in order to maintain the dryfall properties at 15 feet.

WARRANTY	CAUTION
This product will give full satisfaction if applied according to the manufacturer's instructions. Manufacturer's liability is limited to the replacement of the product and does not include manpower if found defective upon inspection.	-Keep in a dry area between 10° C-30° C

Dispose of the container in an environmentally-friendly manner.

MF Paints inc., 1605 Dagenais BLVD. West Laval, Quebec, H7L 5A3 Customer Service 1-800-363-8034

FT757