

RUST-OLEUM®



3700 SYSTEM DTM ACRYLIC ENAMEL

DESCRIPTION AND USES

The 3700 System DTM Acrylic Enamel is a low-VOC, water based acrylic finish for indoor or outdoor direct-to-metal (DTM) applications, suitable for use in conditions of high relative humidity and/or low temperatures.

The 3700 System complies with USDA FSIS regulatory sanitation performance standards for food establishment facilities. This coating is impervious to moisture and easily cleaned and sanitized.

PRODUCTS

READY-MIXED GLOSS FINISHES

1-Gallon	5-Gallon	Description
3737402	—	Forest Green
3771402	—	Dunes Tan
3777402	—	Chestnut Brown
3779402	3779300*	Gloss Black
3782402	—	Silver Gray
3786402	—	Navy Gray
3792402	3792300	Gloss White
3725402	3725300*	Safety Blue
3744402	—	Safety Yellow
3764402	—	Safety Red
206164	—	Alumi-Non
206165	—	Safety Orange
206166	—	Flat Black
206167	—	Semi-Gloss White

TINT BASES

3707411	3707391	Masstone Base
3708418	3708394	Deep Base
3709417	3709397	Light Base

The tint bases use the Rust-Oleum Water-Based Colorants.

*Made to Order only. Contact Rust-Oleum Customer Service for details.

COMPANION PRODUCTS

PRIMERS

1-Gallon	5-Gallon	Description
3769402	3769300	Red Primer
3781402	3781300	Gray Primer

HARDENER

206201	—	Acrylic Hardener
--------	---	------------------

PRODUCT APPLICATION

SURFACE PREPARATION

ALL SURFACES: Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with Pure Strength® Cleaner/Degreaser item #3599402, commercial detergent or other suitable cleaner. Mold and mildew must be cleaned with a chlorinated cleaner or bleach solution. Rinse thoroughly with fresh water and allow to fully dry. All surfaces must be dry at time of application.

STEEL: Hand tool (SSPC-SP-2) or power tool (SSPC-SP-3) clean to remove loose rust, mill scale, and deteriorated previous coatings. Abrasive blasting to a minimum Commercial Grade (SSPC-SP-6, NACE 3) with a 1-2 mil (25-50µ) surface profile is recommended for optimal performance. Abrasive blast cleaned steel requires two coats of primer.

CONCRETE AND MASONRY: Hand or power tool clean to remove all loose or unsound concrete, masonry, or previous coating. Very dense, non-porous concrete should be acid etched or abrasive blasted to remove the laitance layer and create a surface profile. Allow new concrete to cure for 30 days before coating.

PREVIOUSLY COATED: Previously coated surfaces must be sound and in good condition. Smooth, hard, or glossy finishes should be scarified by sanding to create a surface profile. The Rust-Oleum® 3700 System DTM Acrylic Enamel is compatible with most coatings, but a test patch is suggested. Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause adverse effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH-approved) and proper containment and cleanup. For additional information, contact the U.S.EPA/Lead Information Hotline at 1-800-424-LEAD.

APPLICATION

Apply only when the air and surface temperatures are between 35-100°F (2-38°C) and the surface temperature is at least 5°F (3°C) above the dew point. The relative humidity should not be greater than 95%.

The dry times published on page 3 are under conditions of 70-80°F (21-27°C) and a relative humidity of 50%. At lower temperatures, the dry times will be increased and the full development of the coating's physical properties will take longer. Improved air flow will aid the curing process when temperatures are below 50°F or the relative humidity is greater than 80%.



TECHNICAL DATA

3700 SYSTEM DTM ACRYLIC ENAMEL

PRODUCT APPLICATION (cont.)

EQUIPMENT RECOMMENDATIONS

(Comparable equipment also suitable)

BRUSH: Use a good quality synthetic bristle brush.

ROLLER: Use a good quality lamb's wool or synthetic fiber

AIR-ATOMIZED SPRAY:

Method	Fluid Tip	Fluid Delivery	Atom. Pressure
Pressure	0.055-0.070	12-16 oz./min.	25-60 psi
Siphon	0.055-0.070	—	25-60 psi
HVLP (var.)	0.043-0.070	8-10 oz./min.	10 psi (at tip)

AIRLESS SPRAY:

Fluid Pressure	Fluid Tip	Filter Mesh
1,600-2,400 psi	0.013-0.017	100

THINNING

BRUSH/ROLLER: Normally not required. When necessary, thin with fresh water.

AIR ATOMIZED SPRAY: Up to 1 pint per gallon.

AIRLESS SPRAY: Up to ½ pint per gallon.

CLEAN-UP

Soap and water.

PERFORMANCE CHARACTERISTICS

PENCIL HARDNESS

METHOD: ASTM D3363

RESULT: B

CONICAL FLEXIBILITY

METHOD: ASTM D522

RESULT: >33%

CYCLIC PROHESION

Rating 1-10, 10=best

METHOD: ASTM D5894 2 cycles, 672 hours

RESULT: 10 per ASTM D714 or blistering

RESULT: 9 per ASTM D1654 for corrosion

IMPACT RESISTANCE (direct/reverse)

METHOD: ASTM D2794

RESULT: >160/>160

TABER ABRASION

METHOD: ASTM D4060, CS17 wheels 500 g load, 1000 cycles

RESULT: 42 mg loss

ACCELERATED WEATHERING (% gloss retention)

METHOD: ASTM D4587, QUV Type A bulb, 450 hours

RESULT: 87% retention (color-black)

For chemical and corrosion resistance see page 4 of the Rust-Oleum Industrial Brands Catalog Form #206275.



TECHNICAL DATA

3700 SYSTEM DTM ACRYLIC ENAMEL

PHYSICAL PROPERTIES

		READY-MIXED	TINT BASES
Resin Type		Acrylic dispersion	Acrylic dispersion
Pigment Type		Varies with color	Varies with color
Solvents		Water, propylene glycol	Water, propylene glycol
Weight	Per Gallon	8.5-10.0 lbs.	8.5-9.9 lbs.
	Per Liter	1.0-1.2 kg	1.0-1.2 kg
Solids	By Weight	34-51%	38-44%
	By Volume	35-40%	36-39%
Volatile Organic Compounds		<250 g/l (2.08 lbs./gal.)	<250 g/l (2.08 lbs./gal.)
Recommended Dry Film Thickness (DFT) Per Coat		2-3 mils (50-75 μ)	2-3 mils (50-75 μ)
Wet Film to Achieve DFT		5-8 mils (125-200 μ)	5.0-8.5 mils (125-212.5 μ)
Theoretical Coverage at 1 mil DFT (25 μ)		561-640 sq. ft./gal. (15.0-15.7 m ² /l)	577-626 sq. ft./gal. (14.2-15.4 m ² /l)
Practical Coverage at Recommended DFT (assumes 15% material loss)		160-270 sq. ft./gal. (3.9-6.6 m ² /l)	160-270 sq. ft./gal. (3.9-6.6 m ² /l)
Dry Times at 70-80°F (21-27°C) and 50% rel. hum.	Tack-free	1-2 hours	1-2 hours
	Handle	2-4 hours	2-4 hours
	Recoat	1-3 hours	1-3 hours
Dry Heat Resistance		200°F (93°C)	200°F (93°C)
Shelf Life		5 years	5 years
Warning!		PROTECT FROM FREEZING. CAUTION! MAY CAUSE EYE AND SKIN IRRITATION. FOR INDUSTRIAL AND COMMERCIAL USE ONLY. SEE THE PRODUCT MATERIAL SAFETY DATA SHEET (MSDS) AND LABEL WARNINGS FOR ADDITIONAL SAFETY INFORMATION.	

Calculated values are shown and may vary slightly from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.