



Sélection 5371-C

Primer sealer
Latex acrylic

TECHNICAL DATA SHEET

DESCRIPTION

Selection 5371 is a latex acrylic primer sealer for indoor use. It is easy to apply, without spattering and dries quickly. **Selection 5371** is designed for residential and maintenance projects.

USE	LIMITATIONS		
This primer is applicable on interior surfaces. Selection 5371 must be applied to surfaces that have been well prepared. It is suitable for new or used surfaces.	Avoid application in all temperatures under 10°C Do not use on flooring Do not mix with other paints Do not apply to places subject to high humidity Do not apply in high traffic areas.		
CHARACTERISTICS	TECHNICAL INFORMATION		
<ul style="list-style-type: none"> Offers excellent leveling and a soft, smooth finish. Exceeds Canadian standards due to its low VOC. 	DRYING TIME	Recoat: 4 hours	To touch: 30 minutes
	At 25° Celsius. Relative humidity at 50%.		
	SURFACE COVERAGE (for 3.78 L)	35 - 42 m ² (375 - 450 ft ²) May vary depending on the surface	
	Recommended film thickness	Wet : 3,6 - 4.3 mils Dry : 1.14 - 1.37 mils	
	Cleaning	Lukewarm soapy water	
	Resin	Latex acrylic	
	Thinner	Water	
	Inflammability	N/A	
	Flash point	N/A	
	% of solids by weight	50%	
	% of solids by volume	32%	
	VOC	<50 g/L	
	GLOSS	60° N/A 85° N/A The value is measured based on the white. The value may vary according to the chosen colour.	

TINTING BASES				
		946 ml	3,78 L	18,9 L
5371-0	White		X	X

SURFACE PREPARATION

The surface must be dry and clean, without dust, oil, grease, rust and soap. On painted surfaces, it is recommended to clean with a degreaser (T.S.P.) in order to eliminate any contaminant that may harm the adhesion or the curing of the product. Thoroughly rinse the entire surface. The surfaces must be well sanded and dusted.

Presence of mold: Clean the affected area with a mixture of 1 part bleach to 3 parts water. Thoroughly rinse the entire surface.

Flaking or peeling paint: Using a scraper, remove the weakened and/or loose paint, then sand the edges of the surface to make it smooth. A repair compound must be used to fill holes and uneven surfaces. Sand with a #100 grit sandpaper.

New drywall: In order to avoid creating an undesirable texture on the drywall, the joint compound must not be sanded excessively.

Concrete/Masonry: Wait until the concrete and/or masonry has cured at least 30 days before painting it.

Aluminum, galvanized metal, and interior ferrous metal: Remove all traces of oxidation (rust), then clean with **Metal Plus 467**, metal conditioner.

Wood: The surface must be sanded with a #80 or #100 grit sandpaper to smoothen the surface.

APPLICATION

This product is ready to be used and does not require dilution. Mix well before use. Apply one coat or two if necessary. Apply one coat or two if necessary. Allow a minimum drying time of 4 hours between each coat for pale colours and 8 hours for dark colours. In order to properly cover the surface, it is recommended to use a 15mm lint free roller and a quality nylon-polyester brush. Clean the brushes and rollers with lukewarm soapy water following their use.

For spray application : Dilute with a maximum of 10% water.

Pressure : 2000 to 2500 lb/in²*

Nozzle : 0.015 – 0.019*

**This data may vary depending on the brand of the equipment manufacturer.*

WARRANTY

This product will give full satisfaction if applied according to the manufacturer's instructions. Manufacturer's liability is limited to the replacement of the product and does not include manpower if found defective upon inspection.

MAINTENANCE

Must be topcoated.

STORAGE

Store the paint in a dry area and maintain temperature between 10°C and 30°C.

CAUTION

- Keep away from children's reach
- Keep lid closed when not in use
- Avoid freezing

" Contact your municipality to dispose of the container in an environmentally-friendly manner "