



TECHNICAL DATA SHEET

PORTICO

INTERIOR / EXTERIOR

C260 SERIES

SATIN / EGGSHELL

100% ACRYLIC

DESCRIPTION

Portico 260 is a supreme quality decorative coating made of 100% acrylic resin that produces a rich, washable satin/eggshell finish. Although it is designed for any room of your house, it is ideal for the bedroom or living room. It is also an excellent paint to cover most exterior surfaces.

USE

This paint can be applied on interior and exterior surfaces. Portico 260 SERIES must be applied to surfaces that have been well prepared and properly primed. This paint is particularly recommended for a variety of substrates including drywall, concrete, galvanized metal, aluminum, masonry, cement and wood. Its satin or eggshell finish offers several benefits: it allows for easy cleaning, which is ideal for maintaining both interior and exterior surfaces, and it provides a subdued sheen that enhances the aesthetic appeal of the painted areas. This combination of durability, ease of maintenance, and aesthetic flexibility makes the Portico 260 a suitable choice for enhancing and protecting a wide range of surfaces in various environments.

CHARACTERISTICS

- Portico 260 clings to well-prepared surfaces without the need for a primer (view SURFACE PREPARATION and RECOMMENDED PRIMER sections)
- During the work, minimal protection is required for baseboards and flooring.
- It is made with a fungicide that will delay the growth of mold.
- The uniformity of the film results in better opacity and a smooth finish for superior leveling.
- Portico 260 has an excellent resistance to cleaning with lukewarm water and mild soap. It will retain its sheen and its colour for a long time.

LIMITATIONS

- Avoid application in all temperatures under 10°C
- Do not apply under direct sunlight
- Do not use on flooring
- Do not apply on alkyd paint
- Do not mix with other paints
- On vinyl siding, do not use a darker colour than the original to prevent deformation of the material.

TECHNICAL DATA

Resin	100% Acrylic			
Thinner	Water			
Cleaning	Lukewarm soapy water			
Flash Point	N/A			
Inflammability	N/A			
Base	1	2	4	5
Solids by weight	49	48,1	44,4	41,8
Solids by volume	35,8	35,7	34,5	33,9
VOC	<50			g/l
Gloss	60°		4,0-7,0	%
Sheen	85°		9-15	%
The value is measured based on the P base. The value may vary according to the chosen colour.				
Standards	CGSB Type 1GP 100, 138 and 209			
	CFIA Approved			

APPLICATION DATA

Surface Coverage		37-46 m ² (400-500) sqft		3,78 L
May vary depending on the surface porosity				
Recommended Film	Wet	3,2-4,0		mils
Thickness	Dry	1,15-1,43		mils
Drying Time	To touch	30		min
	Recoat	4-8		hours
	Exterior	Bases 1 & 2		Bases 4 & 5
		Allow, for dry weather, 36 hours after application		Allow, for dry weather, 72 hours after application
At 25° Celsius - Relative humidity at 50% - May differ depending on the colour				
Application	Brush	√		
	Roller	15		mm
	Spray Airless (Nozzle(0,015-0,019)*	2000-2500		lb/sqin
*This data may vary depending on the equipment of a manufacturer				
Storage	Temperature between		10 and 30	°C
Tinting Bases		Format		Maximum Quantity of colorant
Base	946ML	3,78L	18,9L	OZ/3,78 L
260-1 P Base		√		max. of 2 oz of colorant / 3,78 L
260-2 M Base		√		max. of 5 oz of colorant / 3,78 L
260-4 D Base		√		max. of 8 oz of colorant / 3,78 L
260-5 A Base		√		max. of 12 oz of colorant / 3,78 L



TECHNICAL DATA SHEET

PORTICO

C260 SERIES

SATIN / EGGSHELL

100% ACRYLIC

INTERIOR / EXTERIOR

SURFACE PREPARATION

The surface must be dry and clean, without dust, oil, grease, rust and soap. On painted surfaces, it is recommended to clean with a degreaser (T.S.P.) to eliminate any contaminant that may harm the adhesion or the curing of the product. Thoroughly rinse the entire surface. The surfaces must be well sanded and dusted.

Presence of mold: Clean the affected area with a mixture of 1 part bleach to 3 parts water. Thoroughly rinse the entire surface.

Flaking or peeling paint: Using a scraper, remove the weakened and/or loose paint, then sand the edges of the surface to make it smooth.

A repair compound must be used to fill holes and uneven surfaces. Sand with a #100 grit sandpaper.

New drywall: To avoid creating an undesirable texture on the drywall, the joint compound must not be sanded excessively.

Concrete/Masonry: Wait until the concrete and/or masonry has cured at least 30 days before painting it.

Aluminum, galvanized metal, and interior ferrous metal: Remove all traces of oxidation (rust), then clean with Metal Plus 467, metal conditioner or an appropriate conditioner.

Wood: The surface must be sanded with a #80 or #100 grit sandpaper to smoothen the surface.

New or treated wood having been exposed to bad weather: It is strongly recommended that any apparent or undesirable mold growth be neutralized to prevent peeling. Use a mixture of 1 part bleach to 3 parts water, let stand for 20 minutes to take effect, then rinse and allow the wood to dry for at least 24 hours.

RECOMMENDED PRIMER

Drywall: Use primer; Latex Plus 170 or Proline Eco 7070.

Concrete blocks / rough brick: Apply the Proline 6006 block filler to level the surface or apply the Portico 260 directly.

New Concrete: Apply the Portico 260 directly onto the surface.

New wood: Use the Portico 270.

Pine knots: Seal the pine knots with the Stop Plus 298.

Red cedar and redwood: Apply one to two coats of Block Plus 296 alkyd based.

Aluminum, galvanized metal, and interior ferrous metal: Apply a coat of Adhero Plus 290.

Latex paint: No primer is required.

Alkyd paint: Apply an undercoat of Adhero Plus 290*.

Dark colours: Some dark colours may require the application of a dark tinted primer to improve opacity. Use Adhero Plus 290-2 and 290-4, available in more than 30 colours.

If the surface to be primed is not mentioned, please contact an MF Paints distributor for further recommendations.

**See limitation of Adhero Plus 290*

APPLICATION

This product is ready to be used and does not require dilution. Mix well before use. Apply one coat or two if necessary. Allow a minimum drying time of 4 hours between each coat for light colours and 8 hours for dark colours. To properly cover the surface, it is recommended to use a 15mm lint free roller and a quality nylon-polyester brush. Clean the brushes and rollers with lukewarm soapy water following their use.

For spray application: Dilute with a maximum of 10% water.

Pressure: 2000 to 2500 lb/in²**

Nozzle: 0.015 – 0.019*

***This data may vary depending on the brand of the equipment manufacturer.*

MAINTENANCE

Allow 30 days drying time before proceeding with a first cleaning. Only use mild, non-abrasive cleaners and a soft cloth. Clean the surface using a light, circular motion.

STORAGE

Store the paint in a dry area and maintain temperature between 10°C and 30°C

WARRANTY

This product will give full satisfaction if applied according to the manufacturer's instructions. Manufacturer's liability is limited to the replacement of the product and does not include manpower if found defective upon inspection.

CAUTION

- Keep away from children's reach
- Keep lid closed when not in use
- Avoid freezing

CONTACT YOUR MUNICIPALITY TO DISPOSE OF THE CONTAINER IN AN ENVIRONMENTALLY-FRIENDLY MANNER