



# Portico 263

Flat Black  
100% acrylic

## TECHNICAL DATA SHEET

### DESCRIPTION

Our **Portico 263** flat black finish is a 100% acrylic paint of superior quality for indoor. It is easy to apply, without spattering and dries quickly. The **Portico 263** can be used for commercial, industrial and residential projects.

USE	LIMITATIONS		
This paint is applicable on interior surfaces. <b>Portico 263</b> must be applied to surfaces that have been well prepared and properly primed. It is recommended for surfaces that require a flat black finish.	Avoid application in all temperatures under 10°C Do not use on flooring Wait 30 days before proceeding with the first cleaning Do not mix with other paints.		
CARACTERISTICS	TECHNICAL INFORMATION		
<ul style="list-style-type: none"> <li><b>Portico 263</b> clings to well-prepared surfaces without the need for a primer (view <b>SURFACE PREPARATION</b> and <b>RECOMMENDED PRIMER</b> sections)</li> <li>During the work, minimal protection is required for baseboards and flooring.</li> <li>It is made with a fungicide that will delay the growth of mold.</li> <li>The uniformity of the film results in better opacity and a smooth finish for superior leveling.</li> </ul>	<b>DRYING TIME</b>	Recoat:	
		To touch:	
	4 hours	30 minutes	
	At 25° Celsius Relative humidity at 50% May differ depending on the colour		
	<b>SURFACE COVERAGE (for 3.78 L)</b>	37 - 46 m <sup>2</sup> (400 - 500 ft <sup>2</sup> ) May vary depending on the surface porosity	
	<b>Recommended film thickness</b>	Wet : 3.2 - 4.0 mils Dry : 1.04 - 1.30 mils	
	<b>Cleaning</b>	Lukewarm soapy water	
	<b>Resin</b>	100% acrylic	
	<b>Thinner</b>	Water	
	<b>Inflammability</b>	N/A	
<b>Flash point</b>	N/A		
<b>% of solids by weight</b>	42%		
<b>% of solids by volume</b>	33%		
<b>VOC</b>	<100 g/L		
<b>GLOSS</b>	<b>60°</b>	1 - 1.5%	
<b>Satin/Eggshell</b>	<b>85°</b>	1.5 - 2.5%	
The value is measured based on the white. The value may vary according to the chosen colour.			
STANDARDS			
<b>CGSB</b>	Type 1GP, 100, 138, 209		

FORMAT				
	946 ml	3,78 L	18,9 L	
263-0	Black	X	X	X

<p><b>SURFACE PREPARATION</b></p> <p>The surface must be dry and clean, without dust, oil, grease, rust and soap. On painted surfaces, it is recommended to clean with a degreaser (T.S.P.) in order to eliminate any contaminant that may harm the adhesion or the curing of the product. Thoroughly rinse the entire surface. The surfaces must be well sanded and dusted.</p> <p><b>Presence of mold:</b> Clean the affected area with a mixture of 1 part bleach to 3 parts water. Thoroughly rinse the entire surface.</p> <p><b>Flaking or peeling paint:</b> Using a scraper, remove the weakened and/or loose paint, then sand the edges of the surface to make it smooth. A repair compound must be used to fill holes and uneven surfaces. Sand with a #100 grit sandpaper.</p> <p><b>New drywall :</b> In order to avoid creating an undesirable texture on the drywall, the joint compound must not be sanded excessively.</p> <p><b>Concrete/Masonry:</b> Wait until the concrete and/or masonry has cured at least 30 days before painting it.</p> <p><b>Aluminum, galvanized metal, and interior ferrous metal:</b> Remove all traces of oxidation (rust), then clean with <b>Metal Plus 467</b>, metal conditioner.</p> <p><b>Wood:</b> The surface must be sanded with a #80 or #100 grit sandpaper to smoothen the surface.</p>	<p><b>RECOMMENDED PRIMER</b></p> <p><b>Drywall:</b> Use primer; <b>Proline 6070</b>.</p> <p><b>Concrete blocks/rough brick:</b> Apply the <b>Proline 6006</b> block filler to level the surface or apply the <b>Portico 263</b> directly.</p> <p><b>New Concrete:</b> Apply the <b>Portico 263</b> directly onto the surface.</p> <p><b>New wood:</b> Use the <b>Portico 270</b>.</p> <p><b>Pine knots:</b> Seal the pine knots with the <b>Stop Plus 298</b>.</p> <p><b>Red cedar and redwood:</b> Apply one to two coats of <b>Block Plus 296</b>, alkyd based.</p> <p><b>Aluminum, galvanized metal, and interior ferrous metal:</b> Apply a coat of <b>Adhero Plus 290</b>.</p> <p><b>Latex paint:</b> No primer is required.</p> <p><b>Alkyd paint:</b> Apply an undercoat of <b>Adhero Plus 290*</b>.</p> <p><b>Dark colours:</b> Some dark colours may require the application of a dark tinted primer in order to improve opacity. Use <b>Proline</b> products <b>6070-2</b> and <b>6070-4</b> or <b>Adhero Plus 290-2</b> and <b>290-4</b>, available in more than 30 colours.</p> <p><i>If the surface to be primed is not mentioned, please contact an MF Paints distributor for further recommendations.</i></p> <p><i>* See limitations for <b>Adhero Plus 290</b>.</i></p>
<p><b>APPLICATION</b></p> <p>This product is ready to be used and does not require dilution. Mix well before use. Apply one coat or two if necessary. Allow a minimum drying time of 4 hours between each coat. In order to properly cover the surface, it is recommended to use a 15mm lint free roller and a quality nylon-polyester brush. Clean the brushes and rollers with lukewarm soapy water following their use.</p> <p><b>For spray application :</b> Dilute with a maximum of 10% water.</p> <p><b>Pressure :</b> 2000 to 2500 lb/in<sup>2</sup>*</p> <p><b>Nozzle :</b> 0.015 – 0.019*</p> <p><i>*This data may vary depending on the brand of the equipment manufacturer.</i></p>	<p><b>MAINTENANCE</b></p> <p>Allow a 30 day drying time before proceeding with a first cleaning. Only use mild, non-abrasive cleaners and a soft cloth. Clean the surface using a light, circular motion.</p> <p><b>STORAGE</b></p> <p>Store the paint in a dry area and maintain temperature between 10°C and 30°C.</p>
<p><b>WARRANTY</b></p> <p>This product will give full satisfaction if applied according to the manufacturer's instructions. Manufacturer's liability is limited to the replacement of the product and does not include manpower if found defective upon inspection.</p>	<p><b>CAUTION</b></p> <ul style="list-style-type: none"> <li>• Keep away from children's reach</li> <li>• Keep lid closed when not in use</li> <li>• Avoid freezing</li> </ul>

**" Contact your municipality to dispose of the container in an environmentally-friendly manner "**