



Maintenance

5365-0



Satin

Technical Data Sheet

DESCRIPTION

MAINTENANCE 5365 series is a latex paint with a Satin finish and an excellent opacity that is made to be used for residential and institutional projects.

CHARACTERISTICS

Non spattering

Only a minimum of protection is required to protect baseboards and floors during application.

Superior Uniformity

Superior levelling properties enhance hiding and provide a smoother surface.

Easy application

This paint is easy to apply and spreads easily.

TECHNICAL INFORMATION

Drying Time

Recoat: 4 - 8 hours To touch : 1 hour

At 25° Celsius
Relative humidity at 50%
May differ depending on the colour

Surface Coverage (for 946 ml)

12 – 13 m² (130 – 150 ft²)
May vary depending on the surface porosity

Cleaning

Lukewarm soapy water

Dilution

None

Solids by Weight

48%

Solids by Volume

35%

VOC

<50 g/L

GLOSS

60°	4%
85°	15%

Satin

May vary according to the texture of surface to which it will be applied on

TINTING BASES

White	5365-0
Base P	5365-1
Base M	5365-2
Base D	5365-4
Base A	5365-5

FORMATS

946ml	3.78L	18.9L
	X	X
	X	X
	X	
	X	
	X	

STANDARDS

COLOURS

A super white as well as 1500 MF coloris. There are also an infinity of colours that can be reproduced by computer.

Base P (max. of 2 oz of colorant/ 3,78L)
Base M (max. of 5 oz of colorant/ 3,78L)
Base D (max. of 8 oz of colorant/ 3,78L)
Base A (max. of 12 oz of colorant/ 3,78L)

USE	LIMITATIONS
<ul style="list-style-type: none"> - For interior use - Can be used on unpainted and painted surfaces - Recommended for walls on which a Satin finish is requested - Can be used for residential and institutional projects 	<ul style="list-style-type: none"> - Do not apply if temperature is below 10°C - Do not apply on floors - Wait 15 days before first wash

SURFACE PREPARATION

The surface must be dry and clean, with no traces of flaking, oil, grease, soap, wax, rust and dust. On painted surfaces, it is recommended to clean with T.S.P. (trisodium phosphate) in order to eliminate any contaminant that might harm the adhesion or the hardening of the product. Glossy surfaces must be sanded and dusted before painting.

SUGGESTED PRIMER

Wood:	Seal pine knots with Stop Plus 298 prior to applying the finishing coat
Drywall:	Apply MAINTENANCE 5371-0 primer & sealer
Masonry & concrete:	Apply MAINTENANCE 5371-0 primer & sealer
Ferrous metal:	Apply ISO-RUST 4350 or 4370 rust-resistant primer
Flat latex & alkyd paint:	No primer required
Glossy alkyd paint:	Apply an undercoat of Adhero Plus 290

APPLICATION

Stir thoroughly before use. Apply one or two coats as required. Let dry 4 hours between coats for pale colours and 8 hours for dark colours. A 15mm lint free roller or a quality bristle brush are recommended to enhance its application. For a spray application, dilute with a maximum of 10% water. Clean brushes and rollers with soapy lukewarm water.

WARRANTY	CAUTION
<p>This product will give full satisfaction if applied according to the manufacturer's instructions. Manufacturer's liability is limited to the replacement of the product and does not include manpower if found defective upon inspection.</p>	<ul style="list-style-type: none"> -Keep away from children -Keep in a dry area between 10° C-30° C -Keep lid closed when not used. -Avoid freezing.

Dispose of the container in an environmentally-friendly manner.