



# Technical Data Sheet

# Latex Plus

## Satin / Eggshell



160-0

### DESCRIPTION

**LATEX Plus 160 series** is a Superior Quality decorative interior coating made of acrylic resin that produces a satin/eggshell finish. This paint can be directly applied on new drywall without requiring a primer sealer.

CHARACTERISTICS	TECHNICAL INFORMATION
-----------------	-----------------------

<p><b><u>Non spattering</u></b> Only a minimum of protection is required to protect baseboards and floors during application.</p> <p><b><u>Washable</u></b> The sheen and the colour of the <b>LATEX Plus</b> will not be affected by repeated washings with lukewarm water and mild soap solutions.</p> <p><b><u>Excellent hiding</u></b> With only 2 coats, this paint will hide most colours. To facilitate its application and for better results, use a 15mm lint free roller.</p> <p><b><u>Paint and Primer in 1</u></b> This self-priming paint allows to seal and paint a surface at the same time.</p>	<table border="1" style="width:100%; border-collapse: collapse;"> <tr> <td style="width:30%;"><b>Drying Time</b></td> <td style="width:35%;">Recoat: 4 – 8 hours</td> <td style="width:35%;">To touch : 1 hour</td> </tr> <tr> <td></td> <td colspan="2">At 25° Celsius Relative humidity at 50% May differ depending on the colour</td> </tr> <tr> <td><b>Surface Coverage (for 946 ml)</b></td> <td colspan="2">10.5 – 13.0m<sup>2</sup> (113 -140ft<sup>2</sup>) May vary depending on the surface porosity</td> </tr> <tr> <td><b>Cleaning</b></td> <td colspan="2">Lukewarm soapy water</td> </tr> <tr> <td><b>Dilution</b></td> <td colspan="2">None</td> </tr> <tr> <td><b>Solids by Weight</b></td> <td colspan="2">55%</td> </tr> <tr> <td><b>Solids by Volume</b></td> <td colspan="2">41%</td> </tr> <tr> <td><b>VOC</b></td> <td colspan="2">&lt;100 g/L</td> </tr> <tr> <td rowspan="2"><b>GLOSS Satin/Eggshell</b></td> <td><b>60°</b></td> <td>5 - 8%</td> </tr> <tr> <td><b>85°</b></td> <td>14 - 18%</td> </tr> <tr> <td></td> <td colspan="2">May vary according to the texture of surface to which it will be applied on</td> </tr> </table>	<b>Drying Time</b>	Recoat: 4 – 8 hours	To touch : 1 hour		At 25° Celsius Relative humidity at 50% May differ depending on the colour		<b>Surface Coverage (for 946 ml)</b>	10.5 – 13.0m <sup>2</sup> (113 -140ft <sup>2</sup> ) May vary depending on the surface porosity		<b>Cleaning</b>	Lukewarm soapy water		<b>Dilution</b>	None		<b>Solids by Weight</b>	55%		<b>Solids by Volume</b>	41%		<b>VOC</b>	<100 g/L		<b>GLOSS Satin/Eggshell</b>	<b>60°</b>	5 - 8%	<b>85°</b>	14 - 18%		May vary according to the texture of surface to which it will be applied on	
<b>Drying Time</b>	Recoat: 4 – 8 hours	To touch : 1 hour																															
	At 25° Celsius Relative humidity at 50% May differ depending on the colour																																
<b>Surface Coverage (for 946 ml)</b>	10.5 – 13.0m <sup>2</sup> (113 -140ft <sup>2</sup> ) May vary depending on the surface porosity																																
<b>Cleaning</b>	Lukewarm soapy water																																
<b>Dilution</b>	None																																
<b>Solids by Weight</b>	55%																																
<b>Solids by Volume</b>	41%																																
<b>VOC</b>	<100 g/L																																
<b>GLOSS Satin/Eggshell</b>	<b>60°</b>	5 - 8%																															
	<b>85°</b>	14 - 18%																															
	May vary according to the texture of surface to which it will be applied on																																

TINTING BASES	FORMATS	STANDARDS
---------------	---------	-----------

	<table border="1" style="width:100%; border-collapse: collapse;"> <tr> <th style="width:33%;">946ml</th> <th style="width:33%;">3.78L</th> <th style="width:33%;">18.9L</th> </tr> <tr> <td>White</td> <td>X</td> <td>X</td> </tr> <tr> <td>P Base</td> <td>X</td> <td>X</td> </tr> <tr> <td>M Base</td> <td>X</td> <td>X</td> </tr> <tr> <td>D Base</td> <td>X</td> <td>X</td> </tr> <tr> <td>A Base</td> <td>X</td> <td>X</td> </tr> </table>	946ml	3.78L	18.9L	White	X	X	P Base	X	X	M Base	X	X	D Base	X	X	A Base	X	X	<p><b>CGSB:</b> Type 1GP 100, 209</p>
946ml	3.78L	18.9L																		
White	X	X																		
P Base	X	X																		
M Base	X	X																		
D Base	X	X																		
A Base	X	X																		

### COLOURS

A super white as well as 1500 MF coloris. There are also an infinity of colours that can be reproduced by computer.

- Base P (max. of 2 oz of colorant/ 3,78L)
- Base M (max. of 5 oz of colorant/ 3,78L)
- Base D (max. of 8 oz of colorant/ 3,78L)
- Base A (max. of 12 oz of colorant/ 3,78L)

USE	LIMITATIONS
<ul style="list-style-type: none"> <li>- For interior use</li> <li>- Can be used on unpainted and painted surfaces</li> <li>- Recommended for walls on which a Satin/Eggshell finish is requested.</li> <li>- Can be used for residential, commercial and institutional projects</li> </ul>	<ul style="list-style-type: none"> <li>- Not for exterior use</li> <li>- Do not use on floors</li> <li>- Do not apply if temperature is below 10°C</li> <li>- Wait 15 days before the first wash</li> </ul>

## SURFACE PREPARATION

The surface must be dry and clean, with no traces of flaking, oil, grease, soap, wax, rust and dust. On painted surfaces, it is recommended to clean with T.S.P. (trisodium phosphate) in order to eliminate any contaminant that might harm the adhesion or the hardening of the product. Glossy surfaces must be sanded and dusted before painting.

## SUGGESTED PRIMER

<b>Wood:</b>	Seal pine knots with <b>Stop Plus 298</b> prior to applying the finishing coat
<b>Drywall:</b>	Apply directly on drywall, 2 coats are required. Or apply <b>Latex Plus 170</b> primer & sealer
<b>Masonry &amp; concrete:</b>	Apply <b>Latex Plus 170</b> primer & sealer
<b>Ferrous metal:</b>	Apply <b>ISO-RUST 4350 or 4370</b> rust-resistant primer
<b>Flat latex &amp; alkyd paint:</b>	No primer required
<b>Glossy alkyd paint:</b>	Apply an undercoat of <b>Adhero Plus 290</b>

## APPLICATION

Stir thoroughly before and during use. Apply one or two coats as required. Let dry 4 hours between coats for pale colours and 8 hours for dark colours. A 15mm lint free roller or a quality bristle brush are recommended to enhance its application. For a spray application, dilute with a maximum of 10% water. Clean brushes and rollers with soapy lukewarm water.

WARRANTY	CAUTION
<p>This product will give full satisfaction if applied according to the manufacturer's instructions. Manufacturer's liability is limited to the replacement of the product and does not include manpower if found defective upon inspection.</p>	<ul style="list-style-type: none"> <li>-Keep away from children</li> <li>-Keep in a dry area between 10° C-30° C</li> <li>-Keep lid closed when not used.</li> <li>-Avoid freezing.</li> </ul>

***Dispose of the container in an environmentally-friendly manner.***