



6070 SERIES

Primer Sealer
Super Hide
Acrylic latex

TECHNICAL DATA SHEET

DESCRIPTION

Our **Proline 6070** is a super hide acrylic latex primer sealer for indoor use. It is easy to apply, without spattering and dries quickly. It is formulated to seal new drywall. Tintable bases are available to be coloured in more than 30 colours. This primer was developed to answer the needs of professional painters. The **Proline 6070** can be used for commercial, industrial and residential projects.

USE	LIMITATIONS
This super hide primer sealer is applicable on interior surfaces. It seals and hides repairs in order to obtain a uniform finish once the topcoat is applied. Proline 6070 is recommended for new surfaces such as drywall, concrete, and wood.	Avoid application in all temperatures under 10°C Not for exterior use Do not use on flooring Do not apply on alkyd paint

CARACTERISTICS	TECHNICAL INFORMATION																														
<ul style="list-style-type: none"> Proline 6070 was developed to seal drywall as well as repairs in order to obtain a uniform finish once topcoated. It dries quickly and can be covered after only 3 hours. During the work, minimal protection is required for baseboards and flooring. It provides excellent hiding. Tintable bases are used as a primer for colours lacking hiding power. Proline 6070 can easily be sanded after a drying time of 3 hours without overloading the sandpaper. 	<table border="1"> <tr> <td rowspan="2">DRYING TIME</td> <td>Recoat:</td> <td>To touch:</td> </tr> <tr> <td>4 hours</td> <td>30 minutes</td> </tr> </table> <p>At 25° Celsius Relative humidity at 50% May differ depending on the colour</p> <table border="1"> <tr> <td>SURFACE COVERAGE (for 3.78 L)</td> <td>37 - 46 m² (400 - 500 ft²) May vary depending on the surface porosity</td> </tr> <tr> <td>Recommended film thickness</td> <td>Wet : 3.2 - 4.0 mils Dry : 1.41 - 1.76 mils</td> </tr> <tr> <td>Cleaning</td> <td>Lukewarm soapy water</td> </tr> <tr> <td>Resin</td> <td>Acrylic latex</td> </tr> <tr> <td>Thinner</td> <td>Water</td> </tr> <tr> <td>Inflammability</td> <td>N/A</td> </tr> <tr> <td>Flash point</td> <td>N/A</td> </tr> <tr> <td>% of solids by weight</td> <td>58%</td> </tr> <tr> <td>% of solids by volume</td> <td>44%</td> </tr> <tr> <td>VOC</td> <td><50 g/L</td> </tr> <tr> <td rowspan="2">GLOSS</td> <td>60°</td> <td>N/A</td> </tr> <tr> <td>85°</td> <td>N/A</td> </tr> </table>	DRYING TIME	Recoat:	To touch:	4 hours	30 minutes	SURFACE COVERAGE (for 3.78 L)	37 - 46 m ² (400 - 500 ft ²) May vary depending on the surface porosity	Recommended film thickness	Wet : 3.2 - 4.0 mils Dry : 1.41 - 1.76 mils	Cleaning	Lukewarm soapy water	Resin	Acrylic latex	Thinner	Water	Inflammability	N/A	Flash point	N/A	% of solids by weight	58%	% of solids by volume	44%	VOC	<50 g/L	GLOSS	60°	N/A	85°	N/A
DRYING TIME	Recoat:		To touch:																												
	4 hours	30 minutes																													
SURFACE COVERAGE (for 3.78 L)	37 - 46 m ² (400 - 500 ft ²) May vary depending on the surface porosity																														
Recommended film thickness	Wet : 3.2 - 4.0 mils Dry : 1.41 - 1.76 mils																														
Cleaning	Lukewarm soapy water																														
Resin	Acrylic latex																														
Thinner	Water																														
Inflammability	N/A																														
Flash point	N/A																														
% of solids by weight	58%																														
% of solids by volume	44%																														
VOC	<50 g/L																														
GLOSS	60°	N/A																													
	85°	N/A																													

TINTING BASES	FORMAT	946 ml	3,78 L	18,9 L
6070-0	White		X	X
6070-2	M Base		X	max. of 5 oz of colorant/ 3,78 L
6070-4	D Base		X	max. of 8 oz of colorant/ 3,78 L

STANDARDS	
MPI	Certified Category #50, GPS-1, GPS-2
CGSB	Type 1GP 119
CFIAB	Approved

SURFACE PREPARATION	
<p>The surface must be dry and clean, without dust, oil, grease, rust and soap. On painted surfaces, it is recommended to clean with a degreaser (T.S.P.) in order to eliminate any contaminant that may harm the adhesion or the curing of the product. Thoroughly rinse the entire surface. The surfaces must be well sanded and dusted.</p> <p>Presence of mold: Clean the affected area with a mixture of 1 part bleach to 3 parts water. Thoroughly rinse the entire surface.</p> <p>Flaking or peeling paint: Using a scraper, remove the weakened and/or loose paint, then sand the edges of the surface to make it smooth.</p> <p>A repair compound should be used to fill holes and uneven surfaces. Sand with a grade #100 sanding paper.</p> <p>New drywall : To avoid creating an undesirable texture on the drywall, the joint compound must not be sanded excessively.</p> <p>Concrete/Masonry: Wait until the concrete and/or masonry has cured at least 30 days before painting it.</p> <p>Wood: The surface must be sanded with a grade #80 or #100 sanding paper to smoothen the surface.</p>	
APPLICATION	MAINTENANCE
<p>This product is ready to be used and does not require dilution. Mix well before use. Apply one coat or two if necessary. Allow a minimum drying time of 4 hours between each coat. In order to properly cover the surface, it is recommended to use a 15mm lint free roller and a quality nylon-polyester brush. Clean the brushes and rollers with lukewarm soapy water following their use.</p> <p>For spray application : Dilute with a maximum of 10% water.</p> <p>Pressure : 2000 to 2500 lb/in²*</p> <p>Nozzle : 0.017 – 0.021*</p> <p><i>*This data may vary depending on the brand of the equipment manufacturer.</i></p>	<p>Must be topcoated.</p>
	STORAGE
	<p>Store the paint in a dry area and maintain temperature between 10°C and 30°C.</p>
WARRANTY	CAUTION
<p>This product will give full satisfaction if applied according to the manufacturer's instructions. Manufacturer's liability is limited to the replacement of the product and does not include manpower if found defective upon inspection.</p>	<ul style="list-style-type: none"> • Keep away from children's reach • Keep lid closed when not in use • Avoid freezing

" Contact your municipality to dispose of the container in an environmentally-friendly manner "