



Technical Data Sheet

Proline ECO

Pearl
Zero VOC



7030



DESCRIPTION

PROLINE ECO zero VOC 7030 pearl finish does not contain any volatile organic compounds that can contribute to air pollution. This paint is made of 100% acrylic resin.

CHARACTERISTICS		TECHNICAL INFORMATION																																												
<p>Zero VOC This paint is ideal for LEED certified projects as well as for any other project requiring a zero VOC paint</p> <p>Washable & Durable Proline ECO has an outstanding resistance to washings with lukewarm water and mild soap solutions. It will keep its colour for a long period of time.</p> <p>Mildewcide Contains a fungicide that delays mildew proliferation.</p>		<table border="1"> <tr> <td rowspan="2">Drying Time</td> <td>Recoat: 4 – 8 hours</td> <td colspan="2">To touch : 1 hour</td> </tr> <tr> <td colspan="3">At 25° Celsius Relative humidity at 50% May differ depending on the colour</td> </tr> <tr> <td>Surface Coverage (for 946 ml)</td> <td colspan="3">10.5 – 14m² (113 -150ft²) May vary depending on the surface porosity</td> </tr> <tr> <td>Cleaning</td> <td colspan="3">Lukewarm soapy water</td> </tr> <tr> <td>Dilution</td> <td colspan="3">None</td> </tr> <tr> <td>Solids by Weight</td> <td colspan="3">47%</td> </tr> <tr> <td>Solids by Volume</td> <td colspan="3">34%</td> </tr> <tr> <td>VOC</td> <td colspan="3">Zero</td> </tr> <tr> <td rowspan="2">GLOSS</td> <td>60°</td> <td colspan="2">17 – 23%</td> </tr> <tr> <td>85°</td> <td colspan="2">40 – 50%</td> </tr> <tr> <td>Pearl</td> <td colspan="3">May vary according to the texture of surface</td> </tr> </table>			Drying Time	Recoat: 4 – 8 hours	To touch : 1 hour		At 25° Celsius Relative humidity at 50% May differ depending on the colour			Surface Coverage (for 946 ml)	10.5 – 14m ² (113 -150ft ²) May vary depending on the surface porosity			Cleaning	Lukewarm soapy water			Dilution	None			Solids by Weight	47%			Solids by Volume	34%			VOC	Zero			GLOSS	60°	17 – 23%		85°	40 – 50%		Pearl	May vary according to the texture of surface		
Drying Time	Recoat: 4 – 8 hours	To touch : 1 hour																																												
	At 25° Celsius Relative humidity at 50% May differ depending on the colour																																													
Surface Coverage (for 946 ml)	10.5 – 14m ² (113 -150ft ²) May vary depending on the surface porosity																																													
Cleaning	Lukewarm soapy water																																													
Dilution	None																																													
Solids by Weight	47%																																													
Solids by Volume	34%																																													
VOC	Zero																																													
GLOSS	60°	17 – 23%																																												
	85°	40 – 50%																																												
Pearl	May vary according to the texture of surface																																													
TINTING BASES		FORMATS		STANDARDS																																										
		946ml	3.78L	18.9L	<p>MPI: Type category #43 Type GPS-2 <i>(Master Paint Institute)</i></p>																																									
White	7030-0		X	X																																										
P Base	7030-1		X	X																																										
M Base	7030-2		X																																											
D Base	7030-4		X																																											
A Base	7030-5		X																																											
COLOURS					<p>CFIA: Product approved <i>(Canadian Food Inspection Agency)</i></p>																																									
<p>A super white as well as 1500 MF coloris. There are also an infinity of colours that can be reproduced by computer.</p> <p>Base P (max. of 2 oz of colorant/ 3,78L) Base M (max. of 5 oz of colorant/ 3,78L) Base D (max. of 8 oz of colorant/ 3,78L) Base A (max. of 12 oz of colorant/ 3,78L)</p>																																														

USE	LIMITATIONS
<ul style="list-style-type: none"> - For interior or exterior use - Can be used on new or painted surfaces - Recommended for doors & frames, cabinets, kitchens & washrooms as well as for high level activity areas - Outdoors, it may be used on vertical surfaces such as; fences, garages, cement walls or cement blocks and any other substrate - Suitable for residential, commercial or institutional projects 	<ul style="list-style-type: none"> - Do not apply if temperature is below 10°C - Do not apply on floors - Wait 15 days before the first wash - Do not scrub with recurring or ammonia based products

SURFACE PREPARATION

The surface must be dry and clean, without dust, oil, grease, rust and soap. On painted surfaces, it is recommended to clean with T.S.P. (trisodium phosphate) in order to eliminate any contaminant that might harm the adhesion or the hardening of the product. Glossy surfaces must be sanded and dusted before painting.

SUGGESTED PRIMER

- Wood:** Seal pine knots with **Stop Plus 298** prior to applying the finishing coat
- Drywall or Interior Masonry:** Apply **Proline ECO 7070** primer & sealer or an undercoat of **Proline ECO 7090**
- Ferrous metal:** Apply **ISO-RUST 4350 or 4370** rust-resistant primer
- Flat latex & alkyd paint:** No primer required
- Glossy alkyd paint:** Apply an undercoat of **Proline ECO 7090**

APPLICATION

Stir thoroughly before use. Apply one or two coats as required. Let dry 4 hours between coats for pale colours and 8 hours for dark colours. A 15mm lint free roller or a quality nylon-polyester brush are recommended to enhance its application. For a spray application, dilute with a maximum of 10% water. Clean brushes and rollers with lukewarm soapy water.

WARRANTY	CAUTION
<p>This product will give full satisfaction if applied according to the manufacturer's instructions. Manufacturer's liability is limited to the replacement of the product and does not include manpower if found defective upon inspection.</p>	<ul style="list-style-type: none"> -Keep away from children -Keep in a dry area between 10° C-30° C -Keep lid closed when not used. -Avoid freezing.

Dispose of the container in an environmentally-friendly manner.