

**ISO-RUST****4000 SERIES**

Anti-Rust Paint

Glossy

Alkyd & Polyurethane

TECHNICAL DATA SHEET

DESCRIPTION

Our **ISO-RUST 4000** glossy finish is a superior quality anti-rust paint with polyurethane, for outdoor use. It is formulated to protect metal surfaces. It was developed to answer the needs of professional painters. **ISO-RUST 4000** can be used for commercial, industrial and residential projects.

USE				LIMITATIONS												
This paint is applicable on exterior surfaces. ISO-RUST 4000 must be applied to surfaces that have been well prepared and properly primed. It is recommended for metal surfaces such as, doors, fences, roofs and furniture. Its glossy finish allows for easy cleaning while offering exceptional resistance.				Avoid application in all temperatures under 10°C Do not apply under direct sunlight Do not use on flooring Wait 7 days before proceeding with the first cleaning Do not mix with other paints												
CHARACTERISTICS				TECHNICAL INFORMATION												
<ul style="list-style-type: none"> The excellent adhesion properties offered by ISO-RUST 4000 allow it to be applied on nearly any surface with a proper preparation (view SURFACE PREPARATION and RECOMMENDED PRIMER sections). Its smooth and waterproof finish prevents stain formation which eases maintenance. Due to the presence of polyurethane, ISO-RUST 4000 is very resistant to weathering and wear. It contains reactive pigments that considerably slow down the formation of rust. 				<table border="1"> <tr> <th rowspan="2">DRYING TIME</th> <th>Recoat:</th> <th>To touch:</th> <th colspan="2">Exterior:</th> </tr> <tr> <td>18-24 hours</td> <td>8-16 hours</td> <td colspan="2">Plan for dry weather 36 hours after application</td> </tr> </table> <p>At 25° Celsius Relative humidity at 50% May differ depending on the colour</p>				DRYING TIME	Recoat:	To touch:	Exterior:		18-24 hours	8-16 hours	Plan for dry weather 36 hours after application	
DRYING TIME	Recoat:	To touch:	Exterior:													
	18-24 hours	8-16 hours	Plan for dry weather 36 hours after application													
SURFACE COVERAGE				37 - 46 m ² (400 - 500 ft ²) (for 3.78 L) May vary depending on the surface												
Recommended film thickness				Wet : 3.2 - 4.0 mils Dry : 1.66 - 2.08 mils												
Cleaning				Mineral spirit (MF-SOL 450)												
Resin				Alkyd & polyurethane												
Thinner				Solvent												
Inflammability				Yes												
Flash point				42°C												
% of solids by weight				68%												
% of solids by volume				52%												
VOC				<400 g/L												
GLOSS				60° >80%												
Glossy				85° >90%												
				The value is measured based on the white. The value may vary according to the												
STANDARDS																
CGSB				Type 1GP, 159,61												
CFIA				Approved product												
TINTING BASES FORMAT																
	946 ml	3,78 L	18,9 L													
4000-0 White	X	X														
4000-1 P Base	X	X		max. of 2 oz of colorant / 3,78 L												
4000-2 M Base	X	X		max. of 5 oz of colorant / 3,78 L												
4000-4 D Base	X	X		max. of 8 oz of colorant / 3,78 L												
4000-5 A Base	X	X		max. of 12 oz of colorant / 3,78 L												
PRE-MIXED COLOURS																
<ul style="list-style-type: none"> 4015-0 Burgundy 4025-0 Fire Red 4045-0 Navy Blue 4060-02 Forest Green 4073-0 Medium Grey 4075-0 Orange Peel 4079-0 Terra Cotta 		<ul style="list-style-type: none"> 4090-0 Dark Brown 4095-0 Golden Brown 4099-0 Flat Black 4100-0 Hi-Gloss Black 4510-0 Security Yellow 4573-0 Grey (interior / exterior) 														

SURFACE PREPARATION	RECOMMENDED PRIMER
<p>The surface must be dry and clean, without dust, oil, grease, rust and soap. On painted surfaces, it is recommended to clean with a degreaser (T.S.P.) in order to eliminate any contaminant that may harm the adhesion or the curing of the product. Thoroughly rinse the entire surface. Glossy surfaces must be well sanded and dusted.</p> <p>Rusted metal : Remove rust and flaking paint with a steel brush, a scraper or an emery paper. It is always recommended to clean the surface with a metal rust remover to improve rust inhibition.</p>	<p>Aluminum, galvanized metal: Apply a coat of Adhero Plus 290.</p> <p>Outdoor ferrous metal: Apply a coat of ISO-RUST 4350 Grey or 4370 Steel Red.</p> <p>Latex paint: No primer is required.</p> <p>Alkyd paint: No primer is required.</p> <p><i>If the surface to be primed is not mentioned, please contact an MF Paints distributor for further recommendations.</i></p>
APPLICATION	MAINTENANCE
<p>This product is ready to be used and does not require dilution. Mix well before use. Apply one coat or two if necessary. Allow a minimum drying time of 18 hours between each coat for pale colours and 24 hours for dark colours. In order to properly cover the surface, it is recommended to use a 10mm lint free roller and a quality nylon-polyester brush. Clean the brushes and rollers with mineral spirit (MF-SOL 450) following their use.</p> <p>For spray application : Dilute with a maximum of 10% solvent.</p> <p>Pressure : 2000 to 2500 lb/in²*</p> <p>Nozzle : 0.015 – 0.019*</p> <p><i>*This data may vary depending on the brand of the</i></p>	<p>Allow a 7 day drying time before proceeding with a first cleaning. Only use mild, nonabrasive cleaners and a soft cloth. Clean the surface using a light, circular motion.</p>
	STORAGE
	<p>Store the paint in a dry area and maintain temperature between 10°C and 30°C.</p>

WARRANTY	CAUTION
<p>This product will give full satisfaction if applied according to the manufacturer's instructions. Manufacturer's liability is limited to the replacement of the product and does not include manpower if found defective upon inspection.</p>	<ul style="list-style-type: none"> • Keep away from children's reach • Use only in a well ventilated area • Keep away from flames and sparks • Keep lid closed when not in use • Maintain a good ventilation when applying • Store in a dry place between 10-30°C

" Contact your municipality to dispose of the container in an environmentally-friendly manner "