



# 8030

Pearl-Melamine 100% Acrylic Latex

#### INTERIOR/EXTERIOR

## Technical Data Sheet

### **Description**

Proline 8030 pearl /melamine finish is a 100% acrylic latex paint of superior quality for interior and exterior use. It is easy to apply, without splashing and dries quickly. It was developed to answer the needs of professional painters. The Proline 8030 can be used for commercial, industrial and residential projects

#### Use

Proline 8030 must be applied on prepared and primed surfaces. It is recommended for drywall, concrete, galvanized metal, aluminum, masonry, cement and wood. Its Pear/ finish allows for easy cleaning while offering good resistance for high traffic areas application.

(See Recommended Primer Section)

### **Advantages**

- Optimal adhesion without a primer on prepared surfaces (see surface preparation and recommended primer sections)
- Formulated low spattering, however during application, minimal protection is required for baseboards and flooring
- Has an excellent leveling, that optimize the hiding and achieve a smooth finish
- Has an excellent resistance to cleaning with lukewarm water and mild soap, it will retain its sheen and it has good colour retention.

#### **Limitations**

- Avoid application under 10°C
- Do not apply under direct sunlight
- Do not use on flooring
- Do not mix with other paints
- On vinyl siding, do not use a darker colour than the original in order to prevent deformation of the material.
- Wait 30 days before proceeding with the first cleaning

#### **Technical Data**

| Resin            |                   | 100% Acrylic |     |
|------------------|-------------------|--------------|-----|
| Color            |                   | White, Bases |     |
| Cleaning         |                   | Water        |     |
| Flash point      |                   | N/A          |     |
| Inflammability   |                   | N/A          |     |
| Solids by weight |                   | 47+/-2       | %   |
| Solids by volume |                   | 37+/-2       | %   |
| voc              |                   | <50          | g/l |
| Gloss            | 60°               | 17-23        | %   |
| Sheen            | 85°               | 40-50        | %   |
| Standards        | CGSB Type 1GP 138 | 3-97         |     |

### **Application Data**

| At 25° Celsius                                   |                               |              |           |                                       |        |  |
|--|-------------------------------|--------------|-----------|---------------------------------------|--------|--|
| Relative humidity a                              | t 50%                         |              |           |                                       |        |  |
| May differ dependin                              | g on the colo                 | ur           |           |                                       |        |  |
| Spreading Rate May vary depending on the surface |                               |              |           | 37-46 m <sup>2</sup><br>(400-500sqft) | gallon |  |
| Film Thickness                                   | Wet                           |              |           | 3,2-4,0                               | mils   |  |
|  | Dry                           |              |           | 1,18-1,48                             | mils   |  |
| Drying Time                                      | Tack free                     |              |           | 30                                    | min    |  |
|  | Recoat                        |              |           | 4-8                                   | hours  |  |
|  | Cleaning                      |              |           | 30                                    | days   |  |
|  | Light                         |              |           | 30                                    | hours  |  |
| Application                                      | Brush                         |              |           | 1                                     |        |  |
|  | Roller                        |              |           | 15                                    | mm     |  |
| Max dillution 10%                                | Spray* Nozzle: 0.017 – 0.021* |              | 2000-2500 | lb/po <sup>2</sup>                    |        |  |
| * These data may vary depend                     | ing on the equipme            | nt manufactu | rer       |                                       |        |  |
| Exterior application                             | and conditio                  | Yes          |           |                                       |        |  |
| Bases 0-1-2                                      | No rain after application     |              |           | 36                                    | hours  |  |
| Bases 4-5  | No rain after application     |              |           | 72                                    | hours  |  |
| Storage  | Temperature                   |              |           | 10-30                                 | °C     |  |
| Tinted Bases                                     |                               | Formats      |           |                                       |        |  |
|  | 946ml                         | 3,78L        | 18,9L     |                                       |        |  |
| 8030-0 White                                     |                               | 1            | 1         |                                       |        |  |
| 8030-1 Base P                                    |                               | 1            | 1         | max. 2 oz de colorant/3,78 L          |        |  |
| 8030-2 Base M                                    |                               | 1            | √         | max. 5 oz de colorant/3,78 L          |        |  |
| 8030-4 Base D                                    |                               | 1            |           | max. 8 oz de colorant/3,78 L          |        |  |
| 8030-5 Base A                                    |                               | 1            |           | max. 12 oz de colorant/3,78 L         |        |  |

MF Paints inc., 1605 boul. Dagenais Blv West Laval, Quebec (H7L 5A3) Customer support : 1-800-363-8034



Technical Data Sheet



## INTERIOR/EXTERIOR

8030

Pearl-Melamine 100% Acrylic Latex

### **Surface Preparation**

The surface must be dry and clean, without dust, oil, grease, rust and soap. On painted surfaces, it is recommended to clean with a degreaser (T.S.P.) in order to eliminate any contaminant that may harm the adhesion or the curing of the product. Thoroughly rinse the entire surface. The surfaces must be well sanded and dusted.

**Presence of mold:** Clean the affected area with a mixture of 1 part bleach to 3 parts water. Thoroughly rinse the entire surface.

**Flaking or peeling paint**: Using a scraper, remove the weakened and/or loose paint, then sand the edges of the surface to make it smooth.

A repair compound should be used to fill holes and uneven surfaces. Sand with a grade #100 sanding paper.

**New drywall**: To avoid creating an undesirable texture on the drywall, the joint compound must not be sanded excessively.

**Concrete / Masonry**: Wait until the concrete and/or masonry has cured at least 30 days before painting it.

**Aluminum, galvanized metal, and interior ferrous metal**: Remove all traces of oxidation (rust), then clean with Metal Plus 467, metal conditioner.

**Wood:** The surface must be sanded with a grade #80 or #100 sanding paper to improve adhesion.

New or treated wood having been exposed to bad weather: It is strongly recommended that any apparent or undesirable mold growth be neutralized in order to prevent peeling. Use a mixture of 1 part bleach to 3 parts water, let stand for 20 minutes to take effect, then rinse and allow the wood to dry for at least 24 hours.

#### **Recommended Primer**

**Drywall**: Use primers, Proline 6070 or Proline Eco 7070. **Concrete block / rough brick**: Not needed or apply the Proline 6006 block filler to level the surface

New Concrete: No primer is required.

**New wood:** Use the Adhero Plus 290 or Adhero Hybrid 297. **Pine knots**: Seal the pine knots with the Stop Plus 298. **Red cedar and redwood**: Apply one to two coats of Block Plus 296 alkyd based.

**Aluminum, galvanized metal:** Apply a coat of Adhero Plus 290 or Metal Plus 4700 white.

Interior ferrous metal not rusted: Adhero Hybrid 297

**Latex paint:** No primer is required.

**Alkyd paint**: Apply an undercoat of Adhero Plus 290\* or Adhero Hybrid 297.

**Dark colours**: Some dark colours may require the application of a dark tinted primer in order to improve opacity. Use Proline products 6070-2 and 6070-4 or Adhero Plus 290-2 and 290-4.

\*See limitations for Adhero Plus 290.

### **Application**

This product is ready to be used and does not require dilution. Mix well before use. Apply one coat or two if necessary. Allow a minimum drying time of 4 hours between each coat for pale colours and 8 hours for dark colours. In order to properly cover the surface, it is recommended to use a 15 mm lint free roller and a quality nylon-polyester brush. Clean the brushes and rollers with lukewarm soapy water following their use.

For spray application: May be diluted with a maximum of

10% water.

**Pressure**: 2000 to 2500 lb/in<sup>2\*</sup>

**Nozzle**: 0.017 – 0.021\*

\*This data may vary depending on the brand of the equipment manufacturer.

#### **Maintenance**

This paint requires 30 days drying time before proceeding with a first cleaning. Only use mild, non-abrasive cleaners and a soft cloth. Clean the surface with a light, circular motion.

#### Warranty

This product will give full satisfaction if applied according to the manufacturer's instructions. Manufacturer's liability is limited to the replacement of the product and does not include manpower if found defective upon inspection.

#### **Caution**

- Keep away from children's reach
- Keep lid closed when not in use
- Avoid freezing

Contact your municipality to dispose of the container in an environmentally-friendly manner.