

Technical Data Sheet

INTERIOR/ EXTERIOR

DESCRIPTION

Grip Plus 292 is a universal alkyd-based primer / sealer for interior and exterior use. It hides stains from water damage, soot, ink, pencil. It is easy to apply and dries quickly. The Grip Plus 292 can be used for both commercial and residential projects.

USE

This universal primer / sealer is applicable on interior and exterior surfaces. Grip Plus 292 should be applied to properly prepared new or previously painted surfaces. It can be applied directly to wood, brick, masonry, plaster, stucco, cement and can be recoated in 4 hours. Grip Plus 292 hides water damage stains on acoustic tiles, and some stains commonly found in a home. Can seal the bleeding from plywood, MDF, Masonite. Two coats may be necessary for best results

ADVANTAGES

- Has an excellent adhesion over multiple surfaces.
- Ideal for porous surfaces
- Hides water stains
- Seals MDF and plywood
- Can be sanded after 4 hours drying
- Hides most spots in 1 or 2 coats
- Can be covered with water-based or solvent-based paint

LIMITATIONS

- To seal cedar and redwood use Block Plus 296
- Not designed to block the smell of smoke
- Do not mix with other paints

TECHNICAL DATA

Resin	Alkyd	
Color	White	
Dilution	N/A	
Tool cleaning	Mineral spirit	MF-SOL 450
Flash Point	30,5	°C
Inflammability	yes	
Solids by weight	76	%
Solids by volume	55	%
VOC	<350	g/l
Gloss 60°	N/A	
Sheen 80°	N/A	
Standards	N/A	

APPLICATION DATA

At 25° Celsius		
Relative humidity at 50%		
May differ depending on the colour		
Spreading Rate	33-42 m ² (350-450sqft)	gallon
May vary depending on the surface porosity		
Film Thickness	Wet	3,6-4,6 mils
	Dry	1,96-2,51 mils
Drying Time	Tack free	30 min
	Recoat	4 hours
	Cleaning	N/A days
Application	Brush	√
	Roller	10 mm
	Spray (Buse 0,015-0,019)*	2000-2500 lb/po2
*This data may vary depending on the equipment of a manufacturer		
Exterior	24	heures
Concervation	Temperature	10 et 30 °C
Base	Formats	
	946ml	3,78L 18,9L
292-0	√	√

Technical Data Sheet

INTERIOR/ EXTERIOR

SURFACE PREPARATION

The surface should be dry and clean, free from dust, oil, grease, rust and soap. On an already painted surface, it is recommended to clean with a degreaser (PTS) in order to remove any contaminant that could interfere with the adhesion and the hardening of the product. Rinse the entire surface thoroughly and allow it to dry. Surfaces must be well sanded and dusted.

Presence of mold: Clean the affected area with a mixture of 1 part bleach to 3 parts water. Rinse the entire surface thoroughly and allow it to dry.

Chipping paint: Using a scraper, remove weakened paint, then sand the edges of the surface to make it uniform.

A repair compound should be used to fill holes and uneven surfaces. Sand with # 150 grit sandpaper.

Chipping, chalking or efflorescence paint: Using a scraper, remove weakened paint, then sand the edges of the surface to make it smooth. For chalking and efflorescence neutralize with muriatic acid then scrub with a wire brush and / or by pressure washing. A repair compound should be used to fill holes and uneven surfaces. Sand with # 150 grit sandpaper. Remove sanding residue

Glossy surfaces: Sand to ensure excellent adhesion. Clean sanding residue

Alkyd-based paints: Sand to ensure excellent adhesion. Clean off sanding residue.

Wood: Surface should be sanded with # 80 or # 100 grit sandpaper to improve adhesion.

Concrete / Masonry: Allow concrete / masonry to harden at least 30 days before painting.

New or treated wood that has been exposed to bad weather: It is strongly recommended to neutralize any growth of mold, whether visible or not, in order to avoid peeling. Use a mixture of 1 part bleach to 3 parts water, leave to act for 20 minutes, then rinse and allow a minimum drying time of 24 hours

APPLICATION

This product is ready to use and does not require dilution. Mix well before use. It is recommended to use an anti-felt roller and a quality bristle brush.

Depending on the nature of the substrate to be coated, the drying time of Grip Plus 292 may vary. It is therefore important to wait until the primer coat is completely dry before applying a second coat or covering with a topcoat

Clean the rollers and brushes with mineral spirits (MF-SOL 450) after using them.

For spray application:

Pressure: 2000 to 2500 psi * Nozzle: 0.015 - 0.019 *

* These data may vary depending on the brand of the equipment manufacturer

MAINTENANCE

Must be topcoated.

WARRANTY

This product will give complete satisfaction if applied according to the manufacturer's instructions. In the event that this is found to be defective after inspection, the manufacturer's liability is limited to replacement of the product and does not include labor during application.

CAUTION

- Keep out of the reach of children
- Keep container closed when not in use
- Avoid freezing

Contact your municipality to dispose of the container in an environmentally-friendly manner