

## DESCRIPTION

**Experience 5265** is an acrylic latex paint satin finish, designed for interior application. This paint is easy to apply, no spattering and dries quickly. Experience 5265 can be used for maintenance of residential projects.

## USE

Experience 5265 should be applied to properly prepared and primed surfaces. It is recommended to be used to keep walls in good condition previously painted or primed.

## ADVANTAGES

- Low VOC content
- Offers good leveling and a soft finish
- Easy to apply
- Controlled spattering

## LIMITATIONS

- Do not apply where humidity is high (see 5235)
- Avoid application at temperatures below 10 °C
- Do not use on floors
- Do not mix with other paints
- Avoid frequent and aggressive cleaning

## PREMIXED COLOURS

5281	Carnaval of Québec
5282	Acadie Beach
5283	Monts-Valin
5284	Whistler
5285	Gaspésie
5286	Tadoussac
5287	Hudson Baie
5288	Tremblant

## TECHNICAL DATA

<b>Resin</b>	Latex Acrylic	
<b>Color</b>	White & Teinted Bases	Premix
<b>Solvent</b>	Water	
<b>Flash Point</b>	N/A	
<b>Inflammability</b>	N/A	
<b>Solids by weight</b>	35	%
<b>Solids by volume</b>	25	%
<b>VOC</b>	<100	g/l
<b>Gloss</b>	60°	3,0-7,0 %
<b>Sheen</b>	85°	20-40 %

The value is measured from the white. It may vary depending on the color

## APPLICATION DATA

*At 25° Celsius Relative humidity at 50% May differ depending on the colour			
<b>Spreading Rate</b>		37-44 m <sup>2</sup> (400-475sqft)	gallon
May vary depending on the surface porosity			
<b>Film Thickness</b>	Wet	3,4-4,0	mils
<b>Drying Time*</b>	Tack free	1	hour
	Recoat	4-8	hours
	Cleaning	30	days
	Final cure	30	days
	Brush	√	
<b>Application</b>	Roller	13	mm
	Spray Airless (Nozzle 0,015-0,019)**	2000-2500	lb/sqin
**This data may vary depending on the equipment of a manufacturer			
<b>Exterior application and condition</b>		N/A	
<b>Storage</b>	Temperature between	10 et 30	°C
<b>Tinted Based</b>	<b>Format</b>		
	946ML	3,78L	18,9L
5265-0 White		√	√
5265-1 Base P		√	√
5265-2 Base M		√	
5265-4 Base D		√	
5265-5 Base A		√	

max. 2 oz of colorant/3,78 L  
max. 5 oz of colorant/3,78 L  
max. 8 oz of colorant/3,78 L  
max. 12 oz of colorant/3,78 L



TECHNICAL DATA SHEET

# Experience

5265

SATIN

INTERIOR PAINT

## SURFACE PREPARATION

**The surface should be dry and clean**, free from dust, oil, grease, rust and soap. On painted surface, it is recommended to clean with a degreaser (TSP) in order to remove any contaminant that could interfere with the adhesion and/or the full cure of the product. Rinse the entire surface thoroughly. Surfaces must be well sanded and dusted.

**Presence of mold:** Clean the affected area with a mixture of 1 part bleach to 3 parts of water. Rinse before it dries the entire surface thoroughly and let it dry.

**Flaking or peeling:** Using a scraper, remove weakened paint, then sand the edges of the surface to make it smooth.

A repair compound should be used to fill holes and uneven surfaces. Sand with # 150 grit sandpaper.

**New Drywall:** To avoid creating an unwanted texture on the drywall sheet, joint compound should not be sanded excessively.

**Concrete / Masonry:** Allow concrete / masonry to cure at least 30 days before painting.

**Aluminum, galvanized metal, interior ferrous metal:** Remove all traces of oxidation (rust), then clean with Metal Plus 467, Conditioner for metal

**Wood:** The surface should be sanded with # 80 or # 100 grit sandpaper to improve adhesion

## RECOMMENDED PRIMERS

**New Drywall:** Apply Experience 5271

**Concrete/block / rough brick:** Apply Proline 6006 Block Filler to seal and level the texture of the concrete blocks

**Wood without bleeding:** Apply Protico 270

**Wood with bleeding** such as (cedar, redwood, exotic, plywood, recomposed and glued wood and any wood with bleeding): Apply one to two coats of Block Plus 296 alkyd-based.

**WARNING: WOOD IS A NATURAL MATERIAL AND ALTHOUGH IT IS TREATED, BLEEDING MAY RECAP OVER TIME.**

**Pine knots:** Seal pine knots with Stop Plus 298.

**Aluminum, galvanized metal:** Adhero Plus 290

**Interior metal ferrous not rusted:** Adhero Plus 297

**Latex paint high gloss:** Portico 270

**Alkyd paint:** one coat of Adhero Hybrid 297.

**Dark Colours:** Some dark colors may require the application of a primer tinted in a dark color to improve opacity. Use the products the Adhero Plus 290-2 and 290-4

## APPLICATION

This product is ready to use and does not require dilution. Mix well before use. Apply two coats of paint. Allow 4 hours drying time between coats for light colors and 8 hours for dark colors. In order to properly cover the surface, it is recommended to use a 13 mm lint free roller and a quality nylon-polyester brush. Clean rollers and brushes with warm soapy water after using them.

**For spray application:** Maybe diluted with a maximum of 10% water.

**Pressure:** 2000 to 2500 lb/sqin\*

**Nozzle:** 0.015 – 0.019\*

\*This data may vary depending on the brand of the equipment manufacturer

## MAINTENANCE

The paint requires a minimum drying time of 30 days before proceeding with a first cleaning. It is not designed for recurrent cleaning. Use only water, and a soft cloth. Clean the surface with a light and circular movement.

## WARRANTY

This product will give full satisfaction if applied according to the manufacturer's instructions. Manufacturer's liability is limited to the replacement of the product and does not include manpower if found defective upon inspection

## CAUTION

- Keep away from children's reach
- Keep lid closed when not in use
- Avoid freezing

CONTACT YOUR MUNICIPALITY TO DISPOSE OF THE CONTAINER IN AN ENVIRONMENTALLY-FRIENDLY MANNER